



CERTIFICATION

Page 1 of 2

GRADE	SIZE / QUANTITY	MELT SOURCE / HEAT NUMBER
Ti 6Al-4V ELI	Dim:(ST)7.500" x (LT)7.500" 4.479 Lbs	RTI-Niles 8G56530

SPECIFICATIONS
AMS-6932B

COMPLIANCE STATEMENTS
<p>No weld repair. Mercury free during processing. No exposure to radioactive materials. Material Safety Data Sheets (MSDS) available upon request Melt source - RTI International. Melt method: 2X VAR. Chemistry performed by RTI International Final product testing performed by Product Evaluation Systems, Inc. Bar product was produced from purchased raw material at TSI Titanium by open die forging. Descaled and grit blasted surface finish to tolerances of +0.375", - 0.00" for the ST and LT dimensions Product conforms to the technical requirements of the specification(s) and the requirements of the purchase order. Melted and manufactured in the United States. Product complies with DFARS 252.225-7008, 252.225-7009, and 252.225-7014, Alt 1 TSI Titanium has complied with all producer requirements of AS6279A (4.1.3)</p>

HEAT TREAT CONDITION
Annealed per AMS-H-81200D: 1300F, 2.00 hours at temperature. Air-Cooled.
TSI Titanium is Nadcap accredited for Heat Treating and can be found on the Nadcap Qualified Manufacturers List.

METALLOGRAPHY
<p>Macro and micro acceptable per applicable specifications. Alpha case free.</p> <p>Cross section is outside the scope of the mechanical and metallographic requirements for the listed specification. All reported results are informational and not cause for rejection.</p>

This certificate shall not be reproduced (except in its entirety), and no modifications, additions or deletions shall be made hereto, without the express written consent of TechSpec, Inc. Making, adding or recording any false, misleading, fictitious or fraudulent statements or entries on this document may be punishable as a felony under Federal statutes.

The specifications and additional information set forth in this certificate are accurate with respect to the materials described herein as of the date set forth above. Any subsequent thermo-mechanical or similar processing (including any such processing to change the gauge, condition or specification of materials described herein) shall nullify the information set forth in this certificate and TechSpec, Inc. shall have no responsibility for, and makes no representations or warranties with respect to, any such processing or the materials resulting therefrom.



TITANIUM
SALES, CONVERSION
FORGING, ROLLING

CERTIFICATION

Page 2 of 2

NON-DESTRUCTIVE TESTING

Immersion ultrasonic acceptable per:

AMS-2631E CL. A

AMS-STD 2154C Type 1. CL. A

MIL-STD-2154 Type 1 CL. A

NAS 824 Rev. 1 Gr. A

Inspection performed by West Penn NDT.

Reported rejected areas have been removed. These were primarily the as-forged ends.

HEAT NO.: 8G56530

CHEMICAL ANALYSIS - WGT%

	C	Mn	P	S	Si	Cr	Ni	Cu	Mo	W	Fe
T	0.007										0.177
B	0.006										0.151
	Co	Ti	Al	V	N	Zr	Sn	B	O	H	Y
T	Bal.	Bal.	5.93	3.84	0.004			<0.0010	0.11	0.0004	<0.0010
B	Bal.	Bal.	5.95	3.84	0.004			<0.0010	0.11	0.0010	<0.0010

Beta Transus: T- 1793 B-1793

PHYSICAL ANALYSIS

ID	UTS	.2%YS	% ELONG		%RA	Hardness	Hyd Final - %
	PSI	PSI	Elong 4 D	Elong 5 D			
B1x3L	122,900	111,500	18.6	16.2	32.8	30 HRC	0.0017
B1x3T	126,100	113,700	11.6	11.4	26.4		
T2x3L	123,700	110,400	15.1	12.5	29.9		0.0042

BY: *Mark P. Sobota* 7/31/2018

Mark P. Sobota - Executive Vice-President, QA



This certificate shall not be reproduced (except in its entirety), and no modifications, additions or deletions shall be made hereto, without the express written consent of TechSpec, Inc. Making, adding or recording any false, misleading, fictitious or fraudulent statements or entries on this document may be punishable as a felony under Federal statutes.

The specifications and additional information set forth in this certificate are accurate with respect to the materials described herein as of the date set forth above. Any subsequent thermo-mechanical or similar processing (including any such processing to change the gauge, condition or specification of materials described herein) shall nullify the information set forth in this certificate and TechSpec, Inc. shall have no responsibility for, and makes no representations or warranties with respect to, any such processing or the materials resulting therefrom.



1010 Industrial Blvd.
 New Kensington, PA 15068
 Ph 724-334-1900
 Fax 724-334-9785
 info@westpenntesting.com

Ultrasonic Inspection Report

PO: 128210
 Size: 7.5 x 7.5
 Material: Ti 6-4 ELI
 Order #: 180706
 Heat #: 8G56530



Net Weight: 8501

Type of Test: UT Immersion
 Specifications: AMS 2631 Rev E Class A, MIL-STD-2154 N/C Type 1 Class A, AMS-STD-2154 Rev C Type 1 Class A, NAS 824 Rev 2 Grade A
 Procedure: WP-UT-12 Rev 9
 Acceptance: WP-UT-12 Rev 9 Class A

Total Pieces Inspected	Pieces Accepted	Pieces Rejected	Reason for Rejection
8	0	8	See Maps

The recording of false, fictitious or fraudulent statements or entries on this document may be punishable as a felony under Federal Statutes including Federal Law, Title 18, Chapter 47.
 During the test and inspections, the products furnished against this order have not come in direct contact with asbestos, mercury, or any of its compounds nor with any mercury-containing devices employing a single boundary of containment.
 Testing complies with the specifications listed. Inspection records and special process records are on file and available for review.

Inspector: JSchultheis UT Level 2
 Inspection Date(s): 7/24/2018, 7/25/2018, 7/26/2018, 7/27/2018

Respectfully submitted,

Gregg Pompe NDT Level 3
 WEST PENN TESTING GROUP, INC.
 Please send your comments and concerns to us at feedback@westpenntesting.com



RMI Titanium Company, LLC d/b/a RTI Niles
 A subsidiary of Arconic, Inc.
 Arconic Titanium and Engineered Products
 1000 Warren Ave.
 Niles, OH 44448

30253296 8G56530-01-00

Test Report


ORDER DETAILS

MATERIAL DETAILS

SHIPPING DETAILS

Packing List: 80611369
 Size: 12.500in/317.5 mm
 No. of Pieces: 4
 Piece ID's: B1, T2, T1, B2
 Weight (lbs): 17522 lbs/7,948 kg
 Test Piece: No
 Test Piece Qty: 0
 Customer Test Piece Size: N/A
 Test Piece ID: N/A

Alloy: TI 6-4 ELI
 Melt Method: 2x VAR
 Final Melt Location: Niles, OH, USA
 Final Melt Date: 4/6/2018
 Heat-Lot-SR: 8G56530-01-00
 Material: Forged, Conditioned Ti Bloom
 Ingot Diameter: 36in dia./914.4 mm dia.
 Sponge Source: Osaka



SPECIFICATIONS:

AMS 4930H Chemistry Only, AMS 6932C Chem Only, AMS-T-9047 May 2003 Ti-6Al-4V Chemistry Only, ASTM B348-13 Grade 23 Chemistry Only, ASTM F136-13 Chemistry Only, MIL-T-9047G Am 2 Not. 1 2/8/93 Ti-6Al-4V ELI Chemistry Only, ZES 2A-81R Chemistry Only, PWA 300BP, PWA F-17C 7/1/15, S-1000 5/23/17, S-400 6/3/16

Exceptions: None

FPA'S: N/A

MELTING ONLY FPA'S: N/A

CONCESSIONS/ APPROVALS:

None

Ingot Chemistry

Element	Top	Center	Bottom	Method	Limits
O (%)	0.11	0.12	0.11	ASTM E1409-13	0.13 max
N (%)	0.004	0.004	0.004	ASTM E1409-13	0.03 max
C (%)	0.007	0.006	0.006	ASTM E1941-10	0.08 max
Fe (%)	0.177	0.151	0.151	ASTM E2994-16	0.25 max
Al (%)	5.93	5.96	5.95	ASTM E2994-16	5.50 min, 6.50 max
V (%)	3.94	3.75	3.84	ASTM E2994-16	3.50 min, 4.50 max
B (ppm)	<10	<10	<10	ASTM E2994-16	50 max
Y (ppm)	<10	<10	<10	ASTM E2994-16	50 max
Residual Elements, Each (%)	<0.05	<0.05	<0.05	ASTM E2994-16	0.10 max
Residual Elements, Total (%)	<0.30	<0.30	<0.30	ASTM E2994-16	0.30 max
Ti	BAL.	BAL.	BAL.	ASTM E2994-16	-

Product Chemistry

Element	T1 MR	B1 MR	Method	Limits
H (ppm)	4	10	ASTM E1447-09	120 max

This certificate shall not be reproduced except in full without the written approval of the RMI Titanium Company, LLC lab. The recording of false, fictitious, or fraudulent statements or entries on this document may be punished as a felony under federal law. This is to certify that the above test results are correct as contained in the records of the company and conform to order requirements.



ARCONIC

RMI Titanium Company, LLC d/b/a RTI Niles
A subsidiary of Arconic, Inc.
Arconic Titanium and Engineered Products
1000 Warren Ave.
Niles, OH 44446

30253298 8G56530-01-00

Test Report

Beta Transus - DTA +/- 10 F (+/- 6 C)

Property	T1	B1	Limits
Beta Transus (F)	1793 F	1793 F	-
Beta Transus (C)	978 C	978 C	-

Certification Statements

Material has no weld repair.
 Material is free of mercury, radium, luminous or alpha source materials.
 Unless stated otherwise, all testing performed at RTI Niles, Niles, OH, USA
 Material/Parts controlled to P&W reqs. for LCS per P&W-MCL section F-17
 Tested at an approved GE source satisfying the requirements of S400
 Testing performed in accordance with MCL manual section F-23

Bill Colletta

Bill Colletta

Certifications Specialist

Date: 6/27/2018

This certificate shall not be reproduced except in full without the written approval of the RMI Titanium Company, LLC lab. The recording of false, fictitious, or fraudulent statements or entries on this document may be punished as a felony under federal law. This is to certify that the above test results are correct as contained in the records of the company and conform to order requirements.



PRODUCT EVALUATION SYSTEMS, INC.

637 Donohoe Road, P.O. Box 722, Latrobe, PA 15650

www.PES-Testing.com

PHONE 724-834-8848 FAX 724-834-9151

July 19, 2018



Subject: Microstructural and Macrostructural Evaluation of Titanium Samples

Identification: Techspec, Inc. PO# 128211

PES ID# 93585-560-P259 thru P263

Sample Identification: Material: 6-4 ELI, Heat#: 8G56530, WO# 180706, Size: 7.500" Sq.,
Condition: Annealed

PES Sample ID#: P261 (Disc B1x3), P262 (Disc B1x3), & P263 (Disc B1x3x)

Date Sample Rec'd: 7/16/2018

Dear Mark,

As per above subject and identification, the sample was sectioned, mounted, polished, etched and evaluated per identified specifications for microstructure, alpha case, and macrostructure.

Microstructure Examination:

Typical photomicrographs of Disc B1x3 taken at mid-radius illustrating a microstructure of equiaxed and elongated primary alpha (white areas) in a transformed beta matrix (dark areas) with no continuous network of alpha at prior beta grain boundaries. The specimen is considered to be in conformance with AMS 6932B. PES Etch: ET1 (Krolls)

Alpha Case Examination:

Photomicrographs of Disc B1x3 taken near surface in transverse direction. No evidence of alpha case or other surface contaminations was observed. The sample is in conformance with AMS 6932B. The sample was prepared in accordance with ASTM E3-11 (17) and is considered acceptable. PES Etch: ET1

Macrostructure Examination:

Macrophotographs of Disc B1x3 and Disc B1x3x cross sections taken in transverse direction. The samples were etched in a solution of 300ml of H₂O, 42g HNO₃, and 18g of HF at room temperature for a period of 5 minutes. The procedure was done in accordance with AMS 2643E and is in conformance with AMS 6932B.

If you have any questions, please call me (724-834-8848).

Sincerely,

Tara Matson
Lab Technician



The test report shall not be reproduced except in full, without the written approval of the laboratory; and the recording of false, fictitious or fraudulent statements or entries on the certificate may be punished as a felony under Federal law.



PRODUCT EVALUATION SYSTEMS, INC.

637 Donohoe Road, P.O. Box 722, Latrobe, PA 15650

www.PES-Testing.com

PHONE 724-834-8848 FAX 724-834-9151

CHEMICAL ANALYSIS TEST REPORT

PES ID.: 93585-560-P259 thru P263

PO #: 128211

TEST: Chemical Analysis

Methods(s): ASTM E1447-09(16); PES-C012



DATE REC'D: 7/16/2018

DATE: 7/17/2018

Notes: Specs per AMS 6932B Standards utilized for analysis: AR 649, LECO 502-135

Work Performed By: _____

Erin St. Mars, Chemist

Results as reported: Conforming Non-Conforming

Material: 6-4 BLI 7.500" Sq.

LAB ID: 93585 P259	ANALYSIS	RESULT	METHOD	SPEC	DATE	TIME	TECH
Customer Sample ID:	Hydrogen	17	PPM E1447 LECO	≤ 125	07/17/18	10:41	ES
Sample ID: Bar B1x3 Heat#: 8G56530 WO#: 180706 Condition: Annealed							

MECHANICAL, METALLOGRAPHIC, NONDESTRUCTIVE, CHEMICAL TESTING, AND CONSULTANT SERVICES



ISO 17025



The test report shall not be reproduced except in full, without the written approval of the laboratory; and the recording of false, fictitious or fraudulent statements or entries on the certificate may be punished as a felony under Federal law.

PES-057 REV 6 (2/18)

Page 1 of 1



PRODUCT EVALUATION SYSTEMS, INC.

637 Donohoe Road, P.O. Box 722, Latrobe, PA 15650

www.PES-Testing.com

PHONE 724-834-8848 FAX 724-834-9151

CHEMICAL ANALYSIS TEST REPORT

PES ID.: 93585-560-P259 thru P263

PO #: 128211

TEST: Chemical Analysis

Methods(s): ASTM E1447-09(16); PES-C012



DATE REC'D: 7/16/2018

DATE: 7/17/2018

Notes: Specs per AMS 6932B Standards utilized for analysis: AR 649, LECO 502-135

Work Performed By:

Erica St. Mars, Chemist

Results as reported: Conforming Non-Conforming

Material: 6-4 ELI 7.500" Sq.

LAB ID: 93585 P260	ANALYSIS	RESULT	METHOD	SPEC	DATE	TIME	TECH
Customer Sample ID:	Titanium	42	PPM E1447 LECO	≤ 125	07/17/18	10:55	ES
Sample ID: Bar T2x3 Heat#: 8G56530 WO#: 180706 Condition: Annealed							

MECHANICAL, METALLOGRAPHIC, NONDESTRUCTIVE, CHEMICAL TESTING, AND CONSULTANT SERVICES



The test report shall not be reproduced except in full, without the written approval of the laboratory; and the recording of false, fictitious or fraudulent statements or entries on the certificate may be punished as a felony under Federal law.

PES-057 REV 6 (2/18)

Page 1 of 1

M E C H A N I C A L T E S T R E P O R T

PES ID.: 93585-560-P259 thru P263

PO #: 128211

TEST: Mechanical Properties

TESTING SPEC.: ASTM E8-16a, E18-17e1

TEST EQUIPMENT: U12, E25, H01

MAT'L/SPEC.: 6-4 ELI

DIMENSION: 7.500" Sq.

NOTES: AMS-6932B (Reference)

DATE RECD: 7/16/2018

DATE: 7/18/2018

TESTED BY:

Matth Maruschok
Mat Maruschok, Lab Technician



CONFORMANCE/NONCONFORMANCE/AS REPORTED: As Reported

CUSTOMER BAR ID:	Bar B1x3	Bar T2x3	Disc B1x3
CUSTOMER HEAT NO.:	8G56530	8G56530	8G56530
CONDITION:	Annealed	Annealed	Annealed
TSI WORK ORDER:	180706	180706	180706
SPECIMEN ORIENTATION:	Longitudinal	Longitudinal	Transverse
PES SPECIMEN ID:	P259	P260	P261-1
Original Specimen Diameter (inches)	0.349	0.350	0.352
Ultimate Tensile Strength (ksi)	122.9	123.7	126.1
0.2% Offset Yield Strength (ksi)	111.5	110.4	113.7
Upper Yield Strength (ksi)			
Original Gage Length 4D (inches)	1.400	1.400	1.400
Elongation Increase 4D (%)	18.6	15.1	11.6
Original Gage Length 5D (inches)	1.750	1.750	1.750
Elongation Increase 5D (%)	16.2	12.5	11.4
Reduction of Area (%)	32.8	29.9	26.4
Test Comment Code(s)	N	N	N
CUSTOMER BAR ID:	Disc B1x3		
PES SPECIMEN ID:	P261-2		
Hardness (mid-radius)	30 HRC		
Test Comment Code(s)	N		

N = No comment(s).

MECHANICAL, METALLOGRAPHIC, NONDESTRUCTIVE, CHEMICAL TESTING, AND CONSULTANT SERVICES



ISO 17025

The test report shall not be reproduced except in full, without the written approval of the laboratory; and the recording of false, fictitious or fraudulent statements or entries on the certificate may be punished as a felony under Federal law.

PES-052 REV 1 (3/08)

Page 1 of 1